

## KERMAN AZARMAHAN REFRACTORIES CO.

## **Ladle Filler Sands Data Sheets**

Products Names: KazarSand-LF-Cr38 (Carbon-Coated)

Main Raw Materials Cr<sub>2</sub>O<sub>3</sub>/SiO<sub>2</sub>

Particle Size  $0.15 \le d_{90} \le 1.18 \text{ mm}$ 

Maximum Service Temperature 1700°C

Refractoriness (ASTM C24) 37 (1820°C)

**Type of Delivery Dry** (5 kg plastic bags in a 1000 kg laminated big bag)

Shelf Life 12 Months (When stored dry in a cool, dry warehouse)

Bulk density 2-2.4 g/cc

## Chemical Analysis (ICP Method, Wt. %)

Cr<sub>2</sub>O<sub>3</sub> min 37 SiO<sub>2</sub> max 19 C max 1

## <u>Description:</u>

Ladle filler sands of KAZAR are the mixtures of high purity refractory materials that are filled in the nozzle of sliding gate system. The main goal is to achieve a high free opening ratio and prevention of clogging when the sliding gate is opened. The engineers at KAZAR control the most important factor to obtain this goal that is sintering layer between the molten and upside of the sand.

The size of the sands depends on ladle size so it can be change based on requests.

The technical data represent the average of the current production. During the test has to be considered a fluctuation of these values  $\pm$  5%

044 DATE: 2023/26/04